

MEGASORBTM VET

Polyglycolic Acid Suture

Properties

- Retention of 70% - 80% knot tensile strength after 14 days
- Retention of 50% knot tensile strength after 21 days
- Complete mass absorption within 60 to 90 days

Indications


- Gastrointestinal procedures
- Gynaecology procedures
- Ophthalmic procedures
- Skin closure (intracutaneous, subcutaneous)
- Ligatures
- Abdominal Wall
- Muscles

Advantages

- High tensile strength
- Excellent knotting ability
- Smooth passage through tissue
- Easy handling



Product Overview

Presentation/Format	: Needed suture packed in a Dozen box Non-needed suture packed in a cassette
Structure	: Multifilament, Braided
Colour	: Dyed, Undyed
	
Chemical composition	: Polyglycolic acid
Coating	: Polycaprolactone and Calcium Stearate
Sizes	: Violet - USP 8/0 (metric 0.4) - USP 2 (metric 5) : Undyed - USP 6/0 (metric 0.7) - USP 2 (metric 5)
Type of absorption	: Hydrolysis
Sterilisation	: Ethylene oxide