

MITSU FSTTM VET

POLYLACTIN 910 Fast Suture

Properties

- Retention of 50% knot tensile strength after 5 days
- Complete mass absorption within 42 days

Indications

- Gynaecology/Obstetric procedures (e.g.: episiotomy repair)
- Ophthalmic procedures (e.g.: conjunctiva suturing)
- Odontology procedures (e.g.: oral mucosa)
- Skin closure (intracutaneous, subcutaneous)
- Ligatures

Advantages

- High initial tensile strength
- Predictable and constant degradation rate
- Excellent knot security
- Excellent handling properties
- Quick mass absorption



Product Overview

Presentation/Format	: Dozen suture packed in a Dozen box
Structure	: Multifilament, Braided
Colour	: Undyed
Chemical composition	: Poly(glycolide/l-lactide) 90/10
Sizes	: USP 6/0 (metric 0.7) - USP 1 (metric 4)
Type of absorption	: Hydrolysis
Sterilization	: Gamma radiation